

Chosun Refractories SP-70W High-Adhesion Mortar

Category : Ceramic

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-SP-70W-High-Adhesion-Mortar.php

Physical Properties	Metric	English	Comments
Grain Size	75 µm	75 µm	50% ≤ 0.075 mm
	500 µm	500 µm	2% ≥ 0.50 mm

Mechanical Properties	Metric	English	Comments
Adhesive Bond Strength	4.905 MPa	711.4 psi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	5.886 MPa	853.7 psi	
	@Temperature 500 °C, Time 10800 sec	@Temperature 932 °F, Time 3.00 hour	
	6.867 MPa	996.0 psi	
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	

Descriptive Properties	Value	Comments
Chemical Analysis(%)	70=, 2=	
Main Applications	General Brick Incinerator Brick	
Refractoriness (SK),Al2O3,Fe2O3	38=	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China