

Chosun Refractories TCH-175SV Torpedo Castable

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-TCH-175SV-Torpedo-Castable.php

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.004905 GPa	0.7114 ksi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	0.005886 GPa	0.8537 ksi	
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	
	0.007848 GPa	1.138 ksi	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	
Compressive Strength	19.6 MPa	2840 psi	Cold Crushing Strength
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	29.4 MPa	4270 psi	Cold Crushing Strength
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	
	39.2 MPa	5690 psi	Cold Crushing Strength
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	1650 °C	3000 °F	limited
Shrinkage	-0.150 %	-0.150 %	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	
	-0.0900 %	-0.0900 %	
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	
	-0.0600 %	-0.0600 %	
	@Temperature 110 °C,	@Temperature 230 °F,	

Thermal Properties	Time 86400 sec Metric	Time 24.0 hour English	Comments
--------------------	--------------------------	---------------------------	----------

Component Elements Properties	Metric	English	Comments
Al2O3	75 %	75 %	
SiC	15 %	15 %	
SiO2	5.0 %	5.0 %	

Descriptive Properties	Value	Comments
Installation Method	Ramm,vibrating	
Material Required for Estimating(kg/?)	2,600	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China