

## Chosun Refractories TCH-175Y Torpedo Castable

Category : Ceramic , Oxide , Aluminum Oxide

### Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chosun-Refractories-TCH-175Y-Torpedo-Castable.php](http://www.lookpolymers.com/polymer_Chosun-Refractories-TCH-175Y-Torpedo-Castable.php)

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.005886 GPa	0.8537 ksi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	0.007848 GPa	1.138 ksi	
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	
	0.00981 GPa	1.42 ksi	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	
Compressive Strength	34.3 MPa	4980 psi	Cold Crushing Strength
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	49.0 MPa	7110 psi	Cold Crushing Strength
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	
	58.8 MPa	8530 psi	Cold Crushing Strength
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	1650 °C	3000 °F	limited
Shrinkage	-0.0300 %	-0.0300 %	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	0.50 %	0.50 %	
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	
	1.5 %	1.5 %	
	@Temperature 1500 °C,	@Temperature 2730 °F,	

Thermal Properties	Time 10800 sec Metric	Time 3.00 hour English	Comments
--------------------	--------------------------	---------------------------	----------

Component Elements Properties	Metric	English	Comments
-------------------------------	--------	---------	----------

Al2O3	75 %	75 %	
SiO2	15 %	15 %	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Installation Method	Casting, Vibrating	
Material Required for Estimating(kg/?)	2,650	
Water Required for Casting(%)	6.0	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China