

Clariant Renol CP-MF-9 Acetal Copolymer

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

Material Notes:

Data provided by Clariant Masterbatches

Order this product through the following link:

http://www.lookpolymers.com/polymer_Clariant-Renol-CP-MF-9-Acetal-Copolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.41 g/cc	1.41 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.022 cm/cm	0.022 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.018 cm/cm	0.018 in/in	ASTM D955
Melt Flow	9.0 g/10 min @Load 2.16 kg, Temperature 190 °C	9.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	60.7 MPa	8800 psi	ASTM D638
Flexural Yield Strength	97.9 MPa	14200 psi	ASTM D790
Flexural Modulus	2.55 GPa	370 ksi	ASTM D790
Izod Impact, Notched	0.694 J/cm @Temperature 22.8 °C	1.30 ft-lb/in @Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	160 °C	320 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	191 - 204 °C	375 - 400 °F	
Mold Temperature	65.6 - 79.4 °C	150 - 175 °F	
Injection Pressure	4.96 - 8.27 MPa	720 - 1200 psi	Secondary
	8.27 - 13.8 MPa	1200 - 2000 psi	Initial
Back Pressure	0.000 - 0.345 MPa	0.000 - 50.0 psi	

Processing Properties	Metric	English	Comments
Screw Speed	20 - 50 rpm	20 - 50 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China