

Colorite Polymers CS1521SC Non Lead Wire and Cable Vinyl Compound

Category: Polymer, Thermoplastic, Vinyl (PVC), PVC, Wire and Cable Grade

Material Notes:

Description: Colorite specialty wire and cable compounds feature low smoke properties, excellent flame retardance, low temperature flexibility, and resistance to abrasion and chemicals. All are available in UL and non-UL grades. In addition, the engineering-grade thermoplastic elastomers we offer can stand up to the most demanding applications . . . while providing the most desirable performance characteristics at a cost that's more affordable than "ordinary" elastomers. Typical Applications: Clear jacket for service cords and SPTInformation provided by Colorite Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Colorite-Polymers-CS1521SC-Non-Lead-Wire-and-Cable-Vinyl-Compound.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|-----------|-----------|
| Specific Gravity | 1.21 g/cc | 1.21 g/cc | ASTM D792 |
| Loss On Ignition | 25 % | 25 % | ASTM 2863 |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|----------|----------|--------------------|
| Hardness, Shore A | 90 | 90 | 10 sec; ASTM D2240 |
| Tensile Strength, Ultimate | 18.6 MPa | 2700 psi | ASTM D412 |
| Elongation at Break | 330 % | 330 % | ASTM D412 |

| Thermal Properties | Metric | English | Comments | |
|----------------------------------|----------|----------|-----------|--|
| Maximum Service Temperature, Air | 105 °C | 221 °F | | |
| Brittleness Temperature | -22.0 °C | -7.60 °F | ASTM D746 | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China