

## Colorite Polymers Elastichem 7011TX-02 Vinyl Compound

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Molded

### Material Notes:

Description: All components in Elastichem are sanctioned by the U.S. Food & Drug Administration for food packaging applications under Title 21 of the Code of Federal Regulations. For medical use, complete traceability and lot identification of all components are maintained at Colorite. Low coefficient of friction Low gels Improved physical properties Non-sticking, even at 40 shore A Self-frosting for extrusion Self-frosting for injection molding Excellent resiliency for product requiring peristaltic motion Improved extrusion rates for low durometer compounds (i.e. 40-50A) Information provided by Colorite Polymers.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Colorite-Polymers-Elastichem-7011TX-02-Vinyl-Compound.php](http://www.lookpolymers.com/polymer_Colorite-Polymers-Elastichem-7011TX-02-Vinyl-Compound.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	ASTM D2240
Tensile Strength, Ultimate	18.39 MPa	2667 psi	ASTM D638
Elongation at Break	400 %	400 %	ASTM D638
Modulus of Elasticity	0.00656 GPa	0.952 ksi	ASTM D638

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	-33.3 °C	-27.9 °F	T <sub>f</sub> ; ASTM D746
Brittleness Temperature	-48.2 °C	-54.8 °F	X <sub>T</sub> <sub>b</sub> ; ASTM D746

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China