

ConocoPhillips 320 Gear Oil AGMA Lubricant No. 6 EP

Category : Fluid , Lubricant

Material Notes:

Description: Conoco Gear Oil is a heavy-duty extreme-pressure industrial gear lubricant formulated from high-quality hydrocracked base stocks to provide excellent oxidation inhibition, EP load-carrying capacity, resistance to foaming and rust and corrosion protection. Gear Oil is recommended for use in a variety of enclosed gear set types operating under demanding conditions. Gear Oil has been tested and formally approved by Cincinnati Milacron in accordance with its Lubricant Specifications (ISO 68 to 1000, respectively – P-63, 76, 77, 74, 59, 35 and 78). Gear Oil exceeds the latest AGMA Specification 9005 (replacement for 250.04) and U.S. Steel 224 Specification for enclosed gear lubricants. Gear Oil "M" series are specially formulated for use in enclosed gear sets equipped with mist lubrication systems and are approved by Aluminum Company of America (Alcoa) in accordance with its Lubricant Specifications. Information provided by ConocoPhillips.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ConocoPhillips-320-Gear-Oil-AGMA-Lubricant-No-6-EP.php

Physical Properties	Metric	English	Comments
Density	0.890 g/cc	0.0322 lb/in ³	
Viscosity Measurement	95	95	Viscosity Index
Saybolt Viscosity at 100°F	1722 SUS	1722 SUS	
Saybolt Viscosity at 210°F	118 SUS	118 SUS	
Kinematic Viscosity at 40°C (104°F)	323 cSt	323 cSt	
Kinematic Viscosity at 100°C (212°F)	23.7 cSt	23.7 cSt	
Oxidative Stability	2500 hour	2500 hour	Oxidation Control; ASTM D-2893
ASTM Color	5.0	5.0	

Mechanical Properties	Metric	English	Comments
Four Ball Extreme Pressure, Weld Load	250 kg	551 lb (mass)	
Four Ball Wear	0.350 mm	0.0138 in	
Timken Test	27200 g	60.0 lb	

Thermal Properties	Metric	English	Comments
Pour Point	-20.6 °C	-5.00 °F	
Flash Point	254 °C	490 °F	

Descriptive Properties	Value	Comments
Copper Corrosion	1A	
Emulsion	0	
Emulsion Characteristics (40-40-0)	25 minutes	ASTM D-1401
Foam Control (Sequence I,II,III)	0-0-0	
Free Water, Total	85 ml	ASTM D2711
FZG	12	ASTM D5182, pass, load stage
Water in Oil	0.6 %	ASTM D2711

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China