

ConocoPhillips 68 Super Hydraulic Oil

Category : Fluid , Lubricant

Material Notes:

Description: Conoco Super Hydraulic Oil is a high-quality antiwear hydraulic fluid formulated from premium Conoco hydrocracked base stocks to provide superior water separation, antiwear protection, rust and corrosion inhibition, oxidation resistance and thermal stability. Super Hydraulic Oil is recommended for use in a variety of high-pressure mobile and stationary hydraulic systems utilizing vane, piston or gear pumps, especially where water contamination is a frequent occurrence. Super Hydraulic Oil has been tested and formally approved by Denison Hydraulics in accordance with its premium HF-0 requirements. Super Hydraulic Oil also has been formally approved by Cincinnati Milacron under specifications P-68 (ISO 32), P-70 (46) and P-69 (68). Super Hydraulic Oil exceeds Vickers M-2950-S, Vickers I-286-S and U.S. Steel 127 and 136 requirements. Super Hydraulic Oil is available in a variety of viscosity grades, including two multiviscosity (MV) grades for low temperature operation. Super Hydraulic Oil MV22 and MV32 are high-viscosity index products with exceptionally low pour point and superior low temperature pumpability. Super Hydraulic Oil MV22 and MV32 can be used year-round in hydraulic systems in virtually all climates. Information provided by ConocoPhillips.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ConocoPhillips-68-Super-Hydraulic-Oil.php

Physical Properties	Metric	English	Comments
Density	0.870 g/cc	0.0314 lb/in ³	
Viscosity Measurement	99	99	Viscosity Index
Saybolt Viscosity at 100°F	353 SUS	353 SUS	
Saybolt Viscosity at 210°F	56 SUS	56 SUS	
Kinematic Viscosity at 40°C (104°F)	68 cSt	68 cSt	
Kinematic Viscosity at 100°C (212°F)	8.7 cSt	8.7 cSt	
Oxidative Stability	5500 hour	5500 hour	
ASTM Color	0.50	0.50	

Mechanical Properties	Metric	English	Comments
Four Ball Wear	0.450 mm	0.0177 in	

Thermal Properties	Metric	English	Comments
Pour Point	-33.3 °C	-28.0 °F	
Flash Point	243 °C	470 °F	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Dielectric Strength Electrical Properties	35.0 kV/mm Metric	889 kV/in English	No thickness given. Comments
Descriptive Properties	Value		Comments
Emulsion Characteristics (40-40-0)	10 minutes		
FZG	Pass 10 Stages		
FZG Pass	10		

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China