

ConocoPhillips ANDEROL® FGC 5 Fluid, Synthetic Mechanical Seal Fluid ISO 22

Category : Fluid , Lubricant , Polyalphaolefin (PAO)

Material Notes:

Description: ANDEROL FGC 5 Mechanical Seal Fluid is a synthetic hydrocarbon (PAO) based lubricant. FGC 5 Fluid meets the former H-1 approval requirements of the USDA where incidental food contact can occur. ANDEROL food grade lubricants are approved, recommended and field tested by many OEMs in the food processing, baking, bottling, canning, meat processing and pharmaceutical industries. ANDEROL food grade lubricants are listed by NSF International under "USDA Regulations, Proprietary Substances and Nonfood Compounds." The Islamic Food and Nutrition Council of America (IFANCA) endorses FGC 5 Fluid as being produced in conformity with all requirements of Halal. Information provided by ConocoPhillips.Anderol® is a registered trademark of The Anderol Company.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ConocoPhillips-ANDEROL-FGC-5-Fluid-Synthetic-Mechanical-Seal-Fluid-ISO-22.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.830 g/cc	0.830 g/cc	60°F; ASTM D-1298
Saybolt Viscosity at 100°F	100 SUS	100 SUS	ASTM D-2161
Saybolt Viscosity at 210°F	40 SUS	40 SUS	ASTM D-2161
Kinematic Viscosity at 40°C (104°F)	20.9 cSt	20.9 cSt	ASTM D-445
Kinematic Viscosity at 100°C (212°F)	4.0 cSt	4.0 cSt	ASTM D-445

Mechanical Properties	Metric	English	Comments
Four Ball Wear	0.600 mm	0.0236 in	1 hr. @ 1200 rpm, 75°C (167°F), 40 kg.; ASTM D-4172

Thermal Properties	Metric	English	Comments
Pour Point	-60.0 °C	-76.0 °F	ASTM D-97
Flash Point	240 °C	464 °F	ASTM D-92

Descriptive Properties	Value	Comments
Copper Corrosion	1A	3 hrs. at 100°C, ASTM D130
Demulsibility (40-40-0)	Max 30 minutes	at 54°C, ml oil/water/emulsion, ASTM D1401
Evaporation	Max 1.0 %	ASTM D-972, 22 hrs. @ 99°C (210°F)

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China