

ConocoPhillips Hydroclear® 46 Turbine Oil

Category: Fluid, Lubricant

Material Notes:

Description: Conoco Hydroclear Turbine Oil is a premium rust- and oxidationinhibited turbine oil formulated from exclusive Conoco hydrocracked base stock. Hydroclear Turbine Oil is specially formulated with proprietary additive chemistry to meet the requirements of steam, gas and hydroelectric turbine service. Hydroclear Turbine Oil also can be used successfully in pumps, motors and a variety of other industrial applications where a premium rust- and oxidation-inhibited oil is recommended. Hydroclear Turbine Oil has been tested and formally approved by Cincinnati Milacron under specifications P-38 (ISO 32), P-55 (46) and P-54 (68).Information provided by ConocoPhillips.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ConocoPhillips-Hydroclear-46-Turbine-Oil.php

| Physical Properties | Metric | English | Comments |
|--------------------------------------|------------|---------------------------|-----------------|
| Density | 0.865 g/cc | 0.0313 lb/in ³ | |
| Viscosity Measurement | 100 | 100 | Viscosity Index |
| Saybolt Viscosity at 100°F | 232 SUS | 232 SUS | |
| Saybolt Viscosity at 210°F | 49 SUS | 49 SUS | |
| Kinematic Viscosity at 40°C (104°F) | 45 cSt | 45 cSt | |
| Kinematic Viscosity at 100°C (212°F) | 6.7 cSt | 6.7 cSt | |
| Oxidative Stability | 7500 hour | 7500 hour | ASTM D 943 |
| ASTM Color | 0.50 | 0.50 | |

| Thermal Properties | Metric | English | Comments |
|--|----------|----------|-------------|
| Pour Point | -37.2 °C | -35.0 °F | |
| Rotating Bomb Oxidation Test (RBOT) | 850 min | 850 min | ASTM D 2272 |
| Flash Point | 229 °C | 445 °F | |

| Electrical Properties | Metric | English | Comments |
|-----------------------|---------------|--------------|-------------------------------|
| Dielectric Strength | >= 30.0 kV/mm | >= 762 kV/in | No thickness given; ASTM D877 |

| Descriptive Properties | Value | Comments |
|------------------------------------|------------|----------|
| Emulsion Characteristics (40-40-0) | 10 minutes | |
| Zinc | Max 10 ppm | |



Descriptive Properties Value Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China