

## CoorsTek AD-995 Alumina (nom. 99.5% Al<sub>2</sub>O<sub>3</sub>)

Category : Ceramic , Oxide , Aluminum Oxide

### Material Notes:

Thermal Shock Delta Tc = 200°C - Thermal shock tests are performed by quenching samples in water from different elevated temperatures. Delta Tc is the change in temperature which results in a sharp decrease in the flexural strength of the sample. Corrosion: Although all Coors Ceramics are highly resistant to chemical attack, Coors recommends obtaining specific application data from Coors before design finalization. Data Provided by the manufacturer, Coors Ceramics Co.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_CoorsTek-AD-995-Alumina-nom-995-Al2O3.php](http://www.lookpolymers.com/polymer_CoorsTek-AD-995-Alumina-nom-995-Al2O3.php)

Physical Properties	Metric	English	Comments
Density	3.90 g/cc	0.141 lb/in <sup>3</sup>	ASTM C20
Water Absorption	0.00 %	0.00 %	ASTM C373
Particle Size	6.0 µm	6.0 µm	Average Crystal Size - Thin Section Test

Mechanical Properties	Metric	English	Comments
Knoop Microhardness	14.1	14.1	1000 g load
Hardness, Rockwell 45 N	83	83	GPa
Tensile Strength, Ultimate	262 MPa	38000 psi	ACMA Test #4
Modulus of Elasticity	370 GPa	53700 ksi	ASTM C848
Flexural Strength	379 MPa	55000 psi	ASTM F417
Compressive Strength	2600 MPa	377000 psi	ASTM C773
Poissons Ratio	0.22	0.22	ASTM C848
Fracture Toughness	4.00 - 5.00 MPa-m <sup>1/2</sup>	3.64 - 4.55 ksi-in <sup>1/2</sup>	
Shear Modulus	152 GPa	22000 ksi	Calculated

Thermal Properties	Metric	English	Comments
CTE, linear	8.20 µm/m-°C	4.56 µin/in-°F	ASTM C372
	@Temperature 25.0 - 1000 °C	@Temperature 77.0 - 1830 °F	
Specific Heat Capacity	0.880 J/g-°C	0.210 BTU/lb-°F	ASTM E1269
Thermal Conductivity	30.0 W/m-K	208 BTU-in/hr-ft <sup>2</sup> -°F	ASTM C408

Maximum Service Temperature, Air Thermal Properties	1750 °C Metric	3180 °F English	No Load Comments
<b>Electrical Properties</b>	<b>Metric</b>	<b>English</b>	<b>Comments</b>
Electrical Resistivity	>= 1.00e+14 ohm-cm	>= 1.00e+14 ohm-cm	ASTM D1829
	2.00e+6 ohm-cm	2.00e+6 ohm-cm	ASTM D1829
	@Temperature 1000 °C	@Temperature 1830 °F	
	2.00e+10 ohm-cm	2.00e+10 ohm-cm	ASTM D1829
	@Temperature 500 °C	@Temperature 932 °F	
Dielectric Constant	9.7	9.7	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	8.70 kV/mm	221 kV/in	ac; ASTM D116
Dielectric Loss Index	0.00010	0.00010	at 25°C, 1 MHz; ASTM D2520
<b>Descriptive Properties</b>	<b>Value</b>	<b>Comments</b>	
Color	Ivory		

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China