

## CoorsTek ADS-996 99.6% Alumina Thin Film

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Applications: thin film substrates

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_CoorsTek-ADS-996-996-Alumina-Thin-Film.php](http://www.lookpolymers.com/polymer_CoorsTek-ADS-996-996-Alumina-Thin-Film.php)

Physical Properties	Metric	English	Comments
Density	3.88 g/cc	0.140 lb/in <sup>3</sup>	ASTM-C373
Water Absorption	0.00 %	0.00 %	ASTM-C373
Particle Size	<= 1.2 μm	<= 1.2 μm	Grain Size

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell 45 N	87	87	ASTM-E18
Modulus of Elasticity	372 GPa	54000 ksi	ASTM-C848
Flexural Strength	592 MPa	85900 psi	ASTM-F394
Poissons Ratio	0.20	0.20	ASTM-C848
Shear Modulus	155 GPa	22500 ksi	Calculated

Thermal Properties	Metric	English	Comments
CTE, linear	7.00 μm/m-°C	3.89 μin/in-°F	ASTM-C372
	@Temperature 25.0 - 300 °C	@Temperature 77.0 - 572 °F	
	7.50 μm/m-°C	4.17 μin/in-°F	ASTM-C372
	@Temperature 25.0 - 600 °C	@Temperature 77.0 - 1110 °F	
8.00 μm/m-°C	4.44 μin/in-°F	ASTM-C372	
@Temperature 25.0 - 800 °C	@Temperature 77.0 - 1470 °F		
Thermal Conductivity	8.30 μm/m-°C	4.61 μin/in-°F	ASTM-C372
	@Temperature 25.0 - 1000 °C	@Temperature 77.0 - 1830 °F	
	26.6 W/m-K	185 BTU-in/hr-ft <sup>2</sup> -°F	ASTM-C408
	@Temperature 100 °C	@Temperature 212 °F	

Component Elements Properties	Metric	English	Comments
Al2O3	99.6 %	99.6 %	

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+8 ohm-cm	>= 1.00e+8 ohm-cm	ASTM-D257
	@Temperature 700 °C	@Temperature 1290 °F	
	>= 1.00e+9 ohm-cm	>= 1.00e+9 ohm-cm	ASTM-D257
	@Temperature 500 °C	@Temperature 932 °F	
	>= 1.00e+12 ohm-cm	>= 1.00e+12 ohm-cm	ASTM-D257
@Temperature 300 °C	@Temperature 572 °F		
>= 1.00e+14 ohm-cm	>= 1.00e+14 ohm-cm	ASTM-D257	
@Temperature 25.0 °C	@Temperature 77.0 °F		
>= 1.00e+14 ohm-cm	>= 1.00e+14 ohm-cm	ASTM-D257	
@Temperature 100 °C	@Temperature 212 °F		
Dielectric Constant	9.9	9.9	ASTM-D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	17.7 kV/mm	450 kV/in	ASTM-D149
	@Thickness 1.02 mm	@Thickness 0.0400 in	
	22.6 kV/mm	575 kV/in	ASTM-D116
	@Thickness 0.635 mm	@Thickness 0.0250 in	
Dielectric Loss Index	0.00010	0.00010	
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	

Descriptive Properties	Value	Comments
Color	White	
Permeability	NIL	
Surface Finish - (µin.)	<1	Polished
	<12	Lapped; Profilometer, 0.004" Radius Stylus, 0.30" Cutoff, ANSI/ASME B46.1
	3	As-Fired; Profilometer, 0.004" Radius Stylus, 0.30" Cutoff, ANSI/ASME B46.1

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**