

Corning 0159 Lead Barium Crushed/Powdered Glass

Category : Ceramic , Glass

Material Notes:

Available in mesh sizes 4 through 325 and can be customized. Used for sealing and other applications. Information provided by Corning Incorporated.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Corning-0159-Lead-Barium-CrushedPowdered-Glass.php

Physical Properties	Metric	English	Comments
Density	3.37 g/cc	0.122 lb/in ³	

Thermal Properties	Metric	English	Comments
CTE, linear	9.52 $\mu\text{m}/\text{m}\cdot\text{C}$	5.29 $\mu\text{in}/\text{in}\cdot\text{F}$	
	@Temperature 0.000 - 300 °C	@Temperature 32.0 - 572 °F	
	9.52 $\mu\text{m}/\text{m}\cdot\text{C}$	5.29 $\mu\text{in}/\text{in}\cdot\text{F}$	
	@Temperature 0.000 - 300 °C	@Temperature 32.0 - 572 °F	
Softening Point	645 °C	1190 °F	
Annealing Point	464 °C	867 °F	
Strain Point	423 °C	793 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China