

## **Corning 7059 Barium Borosilicate Glass**

Category: Ceramic, Glass, Optical, Oxide, Silicon Oxide

## **Material Notes:**

Features a low alkali content of less than 0.3%. In thin sheet form, it is an ideal substrate glass that is also used for low-end LCD applications. Also available crushed/powdered for sealing and other uses. Information provided by Corning Incorporated.

Order this product through the following link:

http://www.lookpolymers.com/polymer\_Corning-7059-Barium-Borosilicate-Glass.php

Physical Properties	Metric	English	Comments
Density	2.76 g/cc	0.0997 lb/in³	

Thermal Properties	Metric	English	Comments
	4.60 μm/m-°C	2.56 µin/in-°F	
CTE, linear	@Temperature 0.000 - 300 °C	@Temperature 32.0 - 572 °F	
Softening Point	844 °C	1550 °F	
Annealing Point	639 °C	1180 °F	
Strain Point	593 °C	1100 °F	

	Optical Properties	Metric	English	Comments
	Refractive Index	1.5333	1.5333	
		@Wavelength 589.3 nm	@Wavelength 589.3 nm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China