

Cosmic Plastics 6220 Short Glass Fiber Filled Iso Diallyl Phthalate Molding Compound

Category : Polymer , Thermoset , Diallyl Phthalate (DAP) , Diallyl Phthalate (DAP) Molding Compound, Short Glass Fiber Filled , Filled/Reinforced Thermoset

Material Notes:

Data provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cosmic-Plastics-6220-Short-Glass-Fiber-Filled-Iso-Diallyl-Phthalate-Molding-Compound.php

Physical Properties	Metric	English	Comments
Density	1.79 g/cc	0.0647 lb/in ³	
Apparent Bulk Density	0.720 g/cc	0.0260 lb/in ³	
Water Absorption	0.25 %	0.25 %	48 hrs, 50°C
Linear Mold Shrinkage	0.0010 - 0.0040 cm/cm	0.0010 - 0.0040 in/in	typical.

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	41.0 - 69.0 MPa	5950 - 10000 psi	
Flexural Strength	97.0 MPa	14100 psi	
Compressive Strength	172 MPa	24900 psi	
Izod Impact, Notched	0.450 J/cm	0.843 ft-lb/in	

Thermal Properties	Metric	English	Comments
CTE, linear	25.0 µm/m-°C	13.9 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 1.8 MPa (264 psi)	260 °C	500 °F	Heat Distortion temperature

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+17 ohm-cm	>= 1.00e+17 ohm-cm	
Surface Resistance	>= 1.00e+17 ohm	>= 1.00e+17 ohm	
Dielectric Constant	4.1	4.1	Wet
	@Frequency 1000 Hz	@Frequency 1000 Hz	
	4.1	4.1	Wet
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	

Electrical Properties	Metric	English	Comments
Dissipation Factor	0.0090	0.0090	Wet
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Arc Resistance	0.013	0.013	Wet
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Arc Resistance	155 sec	155 sec	

Processing Properties	Metric	English	Comments
Processing Temperature	135 - 165 °C	275 - 329 °F	Molding temperature

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China