

## Cosmic Plastics 6230 Long Glass Fiber Filled Iso Diallyl Phthalate Molding Compound

Category : Polymer , Thermoset , Diallyl Phthalate (DAP) , Diallyl Phthalate (DAP) Molding Compound, Long Glass Fiber Filled , Filled/Reinforced Thermoset

### Material Notes:

Data provided by the manufacturer.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Cosmic-Plastics-6230-Long-Glass-Fiber-Filled-Iso-Diallyl-Phthalate-Molding-Compound.php](http://www.lookpolymers.com/polymer_Cosmic-Plastics-6230-Long-Glass-Fiber-Filled-Iso-Diallyl-Phthalate-Molding-Compound.php)

Physical Properties	Metric	English	Comments
Density	1.82 g/cc	0.0658 lb/in <sup>3</sup>	
Apparent Bulk Density	0.300 g/cc	0.0108 lb/in <sup>3</sup>	
Water Absorption	0.27 %	0.27 %	48 hrs, 50°C
Linear Mold Shrinkage	0.0010 - 0.0040 cm/cm	0.0010 - 0.0040 in/in	typical.

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	41.0 - 55.0 MPa	5950 - 7980 psi	
Flexural Strength	103 MPa	14900 psi	
Compressive Strength	186 MPa	27000 psi	
Izod Impact, Notched	2.40 J/cm	4.50 ft-lb/in	

Thermal Properties	Metric	English	Comments
CTE, linear	24.0 µm/m-°C	13.3 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 1.8 MPa (264 psi)	260 °C	500 °F	Heat Distortion temperature

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+17 ohm-cm	>= 1.00e+17 ohm-cm	
Surface Resistance	>= 1.00e+17 ohm	>= 1.00e+17 ohm	
Dielectric Constant	4.0	4.0	Wet
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	4.2	4.2	Wet
	@Frequency 1000 Hz	@Frequency 1000 Hz	

Electrical Properties	Metric	English	Comments
Dissipation Factor	0.010	0.010	Wet
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Dissipation Factor	0.013	0.013	Wet
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Arc Resistance	180 sec	180 sec	

Processing Properties	Metric	English	Comments
Processing Temperature	135 - 165 °C	275 - 329 °F	Molding temperature

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China