

## Cosmic Plastics CP7318 Short Glass Fiber Filled Diallyl Phthalate Molding Compound

Category : Polymer , Thermoset , Diallyl Phthalate (DAP) , Diallyl Phthalate (DAP) Molding Compound, Short Glass Fiber Filled , Filled/Reinforced Thermoset

**Material Notes:**

Data provided by the manufacturer.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Cosmic-Plastics-CP7318-Short-Glass-Fiber-Filled-Diallyl-Phthalate-Molding-Compound.php](http://www.lookpolymers.com/polymer_Cosmic-Plastics-CP7318-Short-Glass-Fiber-Filled-Diallyl-Phthalate-Molding-Compound.php)

Physical Properties	Metric	English	Comments
Density	2.00 g/cc	0.0723 lb/in <sup>3</sup>	
Water Absorption	0.20 %	0.20 %	48 hrs, 50°C
Linear Mold Shrinkage	0.0010 - 0.0040 cm/cm	0.0010 - 0.0040 in/in	typical.

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	55.0 - 117 MPa	7980 - 17000 psi	
Flexural Strength	141 MPa	20500 psi	
Compressive Strength	190 MPa	27600 psi	
Izod Impact, Notched	2.40 J/cm	4.50 ft-lb/in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	243 °C	469 °F	Heat Distortion temperature

Processing Properties	Metric	English	Comments
Processing Temperature	135 - 165 °C	275 - 329 °F	Molding temperature

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China