

Cosmic Plastics D45 Mineral Filled Ortho Diallyl Phthalate Molding Compound

Category : Polymer , Thermoset , Diallyl Phthalate (DAP) , Diallyl Phthalate (DAP), Cast, Mineral Filler , Filled/Reinforced Thermoset

Material Notes:

Data provided by the manufacturer.

Order this product through the following link:
http://www.lookpolymers.com/polymer_Cosmic-Plastics-D45-Mineral-Filled-Ortho-Diallyl-Phthalate-Molding-Compound.php

Physical Properties	Metric	English	Comments
Density	1.74 g/cc	0.0629 lb/in³	
Water Absorption	0.40 %	0.40 %	48 hrs, 50°C
Linear Mold Shrinkage	0.0010 - 0.0040 cm/cm	0.0010 - 0.0040 in/in	typical.

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	41.0 MPa	5950 psi	
Flexural Strength	76.0 MPa	11000 psi	
Compressive Strength	165 MPa	23900 psi	
Izod Impact, Notched	0.230 J/cm	0.431 ft-lb/in	

Thermal Properties	Metric	English	Comments
CTE, linear	45.0 µm/m-°C	25.0 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 1.8 MPa (264 psi)	177 °C	351 °F	Heat Distortion temperature
Flammability, UL94	V-0	V-0	
	@Thickness 0.800 mm	@Thickness 0.0315 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+17 ohm-cm	>= 1.00e+17 ohm-cm	
Surface Resistance	>= 1.00e+17 ohm	>= 1.00e+17 ohm	
Dielectric Constant	4.4	4.4	Wet
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	4.7	4.7	Wet
	@Frequency 1000 Hz	@Frequency 1000 Hz	

Electrical Properties	Metric	English	Comments
Dissipation Factor	0.010	0.010	Wet
	@Frequency 1000 Hz	@Frequency 1000 Hz	
	0.017	0.017	Wet
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Arc Resistance	135 sec	135 sec	

Processing Properties	Metric	English	Comments
Processing Temperature	135 - 165 °C	275 - 329 °F	Molding temperature

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China