

## Cosmic Plastics E487 lass Filled Epoxy Molding Compound, Electrical Grade

Category : Polymer , Thermoset , Epoxy , Epoxy, Molded, Glass Fiber Filler , Filled/Reinforced Thermoset

### Material Notes:

Data provided by the manufacturer.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Cosmic-Plastics-E487-lass-Filled-Epoxy-Molding-Compound-Electrical-Grade.php](http://www.lookpolymers.com/polymer_Cosmic-Plastics-E487-lass-Filled-Epoxy-Molding-Compound-Electrical-Grade.php)

Physical Properties	Metric	English	Comments
Density	1.85 g/cc	0.0668 lb/in <sup>3</sup>	
Apparent Bulk Density	0.740 g/cc	0.0267 lb/in <sup>3</sup>	
Water Absorption	0.20 %	0.20 %	48 hrs, 50°C
Linear Mold Shrinkage	0.0010 - 0.0040 cm/cm	0.0010 - 0.0040 in/in	typical.

Mechanical Properties	Metric	English	Comments
Hardness, Barcol	70	70	
Tensile Strength, Ultimate	83.0 MPa	12000 psi	
Flexural Strength	124 MPa	18000 psi	
Flexural Modulus	18.0 GPa	2610 ksi	
Compressive Strength	193 MPa	28000 psi	
Izod Impact, Notched	0.320 J/cm	0.599 ft-lb/in	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.37683 W/m-K	2.6152 BTU-in/hr-ft <sup>2</sup> -°F	
Deflection Temperature at 1.8 MPa (264 psi)	>= 230 °C	>= 446 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	
Dielectric Constant	4.6	4.6	Wet
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	5.2	5.2	Wet

Electrical Properties	@Frequency 1000 Hz Metric	@Frequency 1000 Hz English	Comments
Dielectric Strength	14.0 kV/mm	356 kV/in	Wet, Step by Step
Dissipation Factor	0.0080	0.0080	Wet
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	0.011	0.011	Wet
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Arc Resistance	180 sec	180 sec	

Processing Properties	Metric	English	Comments
Processing Temperature	150 - 175 °C	302 - 347 °F	Molding temperature

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China