

## Cossa Polimeri ESTABLEND 0840 GF Polycarbonate ABS Blend, 20% Glass Filled

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Glass Fiber Filled , Polycarbonate (PC)

### Material Notes:

Polycarbonate and Acrylonitrile Butadiene Styrene blend with 20% glass fiber reinforcement High dimensional stability, high stiffness Information provided by Cossa Polimeri S.r.l.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Cossa-Polimeri-ESTABLEND-0840-GF-Polycarbonate-ABS-Blend-20-Glass-Filled.php](http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTABLEND-0840-GF-Polycarbonate-ABS-Blend-20-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.25 g/cc	0.0452 lb/in <sup>3</sup>	ASTM D 792
Linear Mold Shrinkage	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	ASTM D 955
Melt Flow	3.0 g/10 min @Load 5.00 kg, Temperature 260 °C	3.0 g/10 min @Load 11.0 lb, Temperature 500 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	70.0 MPa	10200 psi	ASTM D 638
Elongation at Break	3.0 %	3.0 %	ASTM D 638
Flexural Modulus	5.50 GPa	798 ksi	ASTM D 790
Izod Impact, Notched	0.800 J/cm @Temperature 0.000 °C	1.50 ft-lb/in @Temperature 32.0 °F	ASTM D 638
	1.00 J/cm @Temperature 23.0 °C	1.87 ft-lb/in @Temperature 73.4 °F	ASTM D 256

Thermal Properties	Metric	English	Comments
Vicat Softening Point	132 °C @Load 5.00 kg	270 °F @Load 11.0 lb	50°C/hr; ASTM D 1525
	142 °C @Load 0.999 kg	288 °F @Load 2.20 lb	50°C/hr; ASTM D 1525
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
	HB	HB	

Thermal Properties	@Thickness 3.20 mm Metric	@Thickness 0.126 in English	Comments
--------------------	------------------------------	--------------------------------	----------

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China