

Cossa Polimeri ESTABLEND PA 1616 GF ABS / Nylon 6 Blend, 8% Glass Filled

Category : Polymer , Thermoplastic , ABS Polymer , Nylon , Nylon 6

Material Notes:

ESTABLEND PA is a blend of acrylonitrile butadiene styrene and polyamide 6.8% glass fiber reinforced High impact strength, high chemical resistance, excellent heat resistance, good dimensional stability Information provided by Cossa Polimeri S.r.l.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTABLEND-PA-1616-GF-ABS-Nylon-6-Blend-8-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ISO 2577
Melt Flow	16 g/10 min @Load 10.0 kg, Temperature 240 °C	16 g/10 min @Load 22.0 lb, Temperature 464 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	46.0 MPa	6670 psi	ISO 527
Elongation at Break	3.5 %	3.5 %	ISO 527
Tensile Modulus	3.00 GPa	435 ksi	ISO 527
Flexural Modulus	2.40 GPa	348 ksi	ISO 178
Izod Impact, Notched	0.100 J/cm @Temperature 23.0 °C	0.187 ft-lb/in @Temperature 73.4 °F	ISO 180/A

Thermal Properties	Metric	English	Comments
Vicat Softening Point	107 °C @Load 5.00 kg	225 °F @Load 11.0 lb	50°C/hr; ISO 306
	180 °C @Load 0.999 kg	356 °F @Load 2.20 lb	50°C/hr; ISO 306
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
	HB @Thickness 3.20 mm	HB @Thickness 0.126 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China