

Cossa Polimeri ESTABLEND PSA 8500 V0 Flame Retardant PC / ASA Blend

Category : Polymer , Thermoplastic , ASA Polymer , Polycarbonate (PC) , Polycarbonate/ASA Alloy, Unreinforced

Material Notes:

Polycarbonate and acrylonitrile styrene acrylate blend Flame retardant class V0, excellent light resistance, high impact resistance, excellent processability Information provided by Cossa Polimeri S.r.l.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTABLEND-PSA-8500-V0-Flame-Retardant-PC-ASA-Blend.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ASTM D 792
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D 955
Melt Flow	25 g/10 min @Load 5.00 kg, Temperature 260 °C	25 g/10 min @Load 11.0 lb, Temperature 500 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	55.0 MPa	7980 psi	ASTM D 638
Tensile Strength, Yield	65.0 MPa	9430 psi	ASTM D 638
Elongation at Break	>= 50 %	>= 50 %	ASTM D 638
Flexural Modulus	2.50 GPa	363 ksi	ASTM D 790
Izod Impact, Notched	5.00 J/cm @Temperature 0.000 °C	9.37 ft-lb/in @Temperature 32.0 °F	ASTM D 256
	5.50 J/cm @Temperature 23.0 °C	10.3 ft-lb/in @Temperature 73.4 °F	ASTM D 256

Thermal Properties	Metric	English	Comments
Hot Ball Pressure Test	125 °C	257 °F	I.E.C. 335-1
Vicat Softening Point	135 °C @Load 5.00 kg	275 °F @Load 11.0 lb	120°C/hr; ASTM D 1525
	140 °C @Load 0.999 kg	284 °F @Load 2.20 lb	120°C/hr; ASTM D 1525
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	

Thermal Properties	Metric	English	Comments
	@Thickness 3.20 mm	@Thickness 0.126 in	
Glow Wire Test	960 °C	1760 °F	I.E.C. 695-2-12

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China