

Cossa Polimeri ESTADIENE 0425 GFS Acrylonitrile Butadiene Styrene, 13% Glass Filled

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 10% Glass Fiber Filled

Material Notes:

ABS with 13% short glass fiberExcellent mechanical and thermal propertiesInformation provided by Cossa Polimeri S.r.l.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTADIENE-0425-GFS-Acrylonitrile-Butadiene-Styrene-13-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in ³	ASTM D 792
Linear Mold Shrinkage	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D 955
Melt Flow	4.0 g/10 min @Load 10.0 kg, Temperature 220 °C	4.0 g/10 min @Load 22.0 lb, Temperature 428 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	26.0 MPa	3770 psi	ASTM D 638
Tensile Strength, Yield	28.0 MPa	4060 psi	ASTM D 638
Elongation at Break	2.0 %	2.0 %	ASTM D 638
Flexural Modulus	2.60 GPa	377 ksi	ASTM D 790
Izod Impact, Notched	1.50 J/cm @Temperature 0.000 °C	2.81 ft-lb/in @Temperature 32.0 °F	ASTM D 638
	1.80 J/cm @Temperature 23.0 °C	3.37 ft-lb/in @Temperature 73.4 °F	ASTM D 256

Thermal Properties	Metric	English	Comments
Vicat Softening Point	98.0 °C @Load 5.00 kg	208 °F @Load 11.0 lb	50°C/hr; ASTM D 1525
	107 °C @Load 0.999 kg	225 °F @Load 2.20 lb	50°C/hr; ASTM D 1525
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
	HB	HB	

Thermal Properties	@Thickness 3.20 mm Metric	@Thickness 0.126 in English	Comments
Glow Wire Test	650 °C	1200 °F	I.E.C. 695-2-1
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China