

Cossa Polimeri ESTADIENE 1030 HT V0 Flame Retardant ABS

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Unreinforced, Flame Retardant

Material Notes:

Acrylonitrile Butadiene Styrene Flame retardant class V0, PBDE free, high thermal resistance, good light resistance, good processability and surface appearance. Information provided by Cossa Polimeri S.r.l.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTADIENE-1030-HT-V0-Flame-Retardant-ABS.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ASTM D 792
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	ASTM D 955
Melt Flow	4.0 g/10 min	4.0 g/10 min	ASTM D 1238
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	
	14 g/10 min	14 g/10 min	ASTM D 1238
	@Load 5.00 kg, Temperature 240 °C	@Load 11.0 lb, Temperature 464 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	40.0 MPa	5800 psi	ASTM D 638
Tensile Strength, Yield	43.0 MPa	6240 psi	ASTM D 638
Elongation at Break	5.0 %	5.0 %	ASTM D 638
Flexural Modulus	2.50 GPa	363 ksi	ASTM D 790
Izod Impact, Notched	0.700 J/cm	1.31 ft-lb/in	ASTM D 638
	@Temperature 0.000 °C	@Temperature 32.0 °F	
	0.900 J/cm	1.69 ft-lb/in	ASTM D 256
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Hot Ball Pressure Test	105 °C	221 °F	I.E.C. 335-1
Vicat Softening Point	110 °C	230 °F	50°C/hr; ASTM D 1525
	@Load 5.00 kg	@Load 11.0 lb	
	121 °C	250 °F	50°C/hr; ASTM D 1525
	@Load 0.999 kg	@Load 2.20 lb	

Thermal Properties	Metric	English	Comments
Flammability, UL94	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-0	V-0	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Glow Wire Test	960 °C	1760 °F	I.E.C. 695-2-1

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China