

## Cossa Polimeri ESTADIENE 1030 V0/Ex Flame Retardant ABS

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Extruded , Acrylonitrile Butadiene Styrene (ABS), Unreinforced, Flame Retardant

### Material Notes:

Acrylonitrile Butadiene Styrene Flame retardant class V0, PBDE free, high impact resistance, high gloss, good light resistance, for extrusion Information provided by Cossa Polimeri S.r.l.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Cossa-Polimeri-ESTADIENE-1030-V0Ex-Flame-Retardant-ABS.php](http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTADIENE-1030-V0Ex-Flame-Retardant-ABS.php)

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ASTM D 792
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	ASTM D 955
Melt Flow	10 g/10 min @Load 10.0 kg, Temperature 220 °C	10 g/10 min @Load 22.0 lb, Temperature 428 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	30.0 MPa	4350 psi	ASTM D 638
Tensile Strength, Yield	38.0 MPa	5510 psi	ASTM D 638
Elongation at Break	6.0 %	6.0 %	ASTM D 638
Flexural Modulus	2.40 GPa	348 ksi	ASTM D 790
Izod Impact, Notched	1.80 J/cm @Temperature 0.000 °C	3.37 ft-lb/in @Temperature 32.0 °F	ASTM D 638
	2.20 J/cm @Temperature 23.0 °C	4.12 ft-lb/in @Temperature 73.4 °F	ASTM D 256

Thermal Properties	Metric	English	Comments
Vicat Softening Point	93.0 °C @Load 5.00 kg	199 °F @Load 11.0 lb	50°C/hr; ASTM D 1525
	102 °C @Load 0.999 kg	216 °F @Load 2.20 lb	50°C/hr; ASTM D 1525
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	
	V-0	V-0	

Thermal Properties	Metric @ Thickness 3.20 mm	English @ Thickness 0.126 in	Comments
Glow Wire Test	960 °C	1760 °F	I.E.C. 695-2-1

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China