

Cossa Polimeri ESTALENE EN 25 C Modified Polyolefin Blend

Category : Polymer , Thermoplastic , Polyolefin

Material Notes:

Formulated for injection molding or extrusion of synthetic corks
Certified according to FDA standards
Information provided by Cossa Polimeri S.r.l.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTALENE-EN-25-C-Modified-Polyolefin-Blend.php

Physical Properties	Metric	English	Comments
Density	0.920 - 0.940 g/cc	0.0332 - 0.0340 lb/in ³	ASTM D 792
Melt Flow	14 - 18 g/10 min @Load 2.16 kg, Temperature 190 °C	14 - 18 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Stress	>= 6.00 MPa	>= 870 psi	
Elongation at Break	>= 500 %	>= 500 %	

Processing Properties	Metric	English	Comments
Processing Temperature	145 - 165 °C	293 - 329 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China