

Cossa Polimeri ESTAPROP 0540 GFC V0 Flame Retardant Polypropylene, 20% Glass Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Glass Fiber Filler , Polypropylene, Flame Retardant

Material Notes:

PP with 20% chemically coupled glass fiber Flame retardant class V0, excellent mechanical characteristics, excellent heat resistance
Information provided by Cossa Polimeri S.r.l.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTAPROP-0540-GFC-V0-Flame-Retardant-Polypropylene-20-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in ³	ASTM D 792
Linear Mold Shrinkage	0.0050 - 0.0080 cm/cm	0.0050 - 0.0080 in/in	ASTM D 955
Melt Flow	5.0 g/10 min @Load 2.16 kg, Temperature 230 °C	5.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	55.0 MPa	7980 psi	ASTM D 638
Elongation at Break	3.0 %	3.0 %	ASTM D 638
Flexural Modulus	5.00 GPa	725 ksi	ASTM D 790
Izod Impact, Notched	0.400 J/cm @Temperature 0.000 °C	0.749 ft-lb/in @Temperature 32.0 °F	ASTM D 638
	0.500 J/cm @Temperature 23.0 °C	0.937 ft-lb/in @Temperature 73.4 °F	ASTM D 256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	135 °C	275 °F	120°C/hr; ASTM D 648
Vicat Softening Point	120 °C @Load 5.00 kg	248 °F @Load 11.0 lb	50°C/hr; ASTM D 1525
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	
	V-0 @Thickness 3.20 mm	V-0 @Thickness 0.126 in	

Thermal Properties Glow Wire Test	850 °C Metric	1750 °F English	Comments I.E.C. 609-2-1
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China