

Cossa Polimeri ESTAPROP H 0560 GFCTG Polypropylene, 30% Mixed Filler

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Glass/Mineral Reinforced

Material Notes:

PP homopolymer 30% mixed filler Good physical and mechanical characteristics Information provided by Cossa Polimeri S.r.l.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTAPROP-H-0560-GFCTG-Polypropylene-30-Mixed-Filler.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ASTM D 792
Linear Mold Shrinkage	0.0060 - 0.0080 cm/cm	0.0060 - 0.0080 in/in	ASTM D 955
Melt Flow	8.0 g/10 min @Load 2.16 kg, Temperature 230 °C	8.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	50.0 MPa	7250 psi	ASTM D 638
Elongation at Break	3.0 %	3.0 %	ASTM D 638
Tensile Modulus	4.70 GPa	682 ksi	ASTM D 638
Flexural Modulus	4.30 GPa	624 ksi	ASTM D 790
Izod Impact, Notched	0.350 J/cm @Temperature -20.0 °C	0.656 ft-lb/in @Temperature -4.00 °F	ASTM D 638
	0.500 J/cm @Temperature 0.000 °C	0.937 ft-lb/in @Temperature 32.0 °F	ASTM D 638
	0.700 J/cm @Temperature 23.0 °C	1.31 ft-lb/in @Temperature 73.4 °F	ASTM D 256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	135 °C	275 °F	120°C/hr; ASTM D 648
Vicat Softening Point	105 °C @Load 5.00 kg	221 °F @Load 11.0 lb	50°C/hr; ASTM D 1525
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Thermal Properties	HB Metric	HB English	Comments
	@Thickness 3.20 mm	@Thickness 0.126 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China