

Cossa Polimeri ESTAPROP H 1660 GFC Polypropylene, 30% Glass Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Glass Fiber Filler

Material Notes:

PP homopolymer 30% chemically coupled glass fiber reinforced High melt flow rate, excellent impact strength Information provided by Cossa Polimeri S.r.l.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTAPROP-H-1660-GFC-Polypropylene-30-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ASTM D 792
Linear Mold Shrinkage	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	ASTM D 955
Melt Flow	15 g/10 min @Load 2.16 kg, Temperature 230 °C	15 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	80.0 MPa	11600 psi	ASTM D 638
Elongation at Break	3.0 %	3.0 %	ASTM D 638
Tensile Modulus	6.60 GPa	957 ksi	ASTM D 638
Flexural Modulus	6.00 GPa	870 ksi	ASTM D 790
Izod Impact, Notched	0.800 J/cm @Temperature -20.0 °C	1.50 ft-lb/in @Temperature -4.00 °F	ASTM D 638
	0.900 J/cm @Temperature 0.000 °C	1.69 ft-lb/in @Temperature 32.0 °F	ASTM D 638
	1.00 J/cm @Temperature 23.0 °C	1.87 ft-lb/in @Temperature 73.4 °F	ASTM D 256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	140 °C	284 °F	120°C/hr; ASTM D 648
Vicat Softening Point	130 °C @Load 5.00 kg	266 °F @Load 11.0 lb	50°C/hr; ASTM D 1525
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Thermal Properties	Metric	English	Comments
	@Thickness 3.20 mm	@Thickness 0.126 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China