

Cossa Polimeri ESTAPROP HK 2540 T8 Polypropylene, 20% Mineral Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Mineral Reinforced

Material Notes:

PP homo/copolymer 20% mineral filler Good physical and mechanical properties Information provided by Cossa Polimeri S.r.l.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTAPROP-HK-2540-T8-Polypropylene-20-Mineral-Filled.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ASTM D 792
Linear Mold Shrinkage	0.012 - 0.014 cm/cm	0.012 - 0.014 in/in	ASTM D 955
Melt Flow	25 g/10 min @Load 2.16 kg, Temperature 230 °C	25 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	22.0 MPa	3190 psi	ASTM D 638
Tensile Strength, Yield	27.0 MPa	3920 psi	ASTM D 638
Elongation at Break	50 %	50 %	ASTM D 638
Tensile Modulus	2.30 GPa	334 ksi	ASTM D 638
Flexural Modulus	2.00 GPa	290 ksi	ASTM D 790
Izod Impact, Notched	0.200 J/cm @Temperature -20.0 °C	0.375 ft-lb/in @Temperature -4.00 °F	ASTM D 638
	0.250 J/cm @Temperature 0.000 °C	0.468 ft-lb/in @Temperature 32.0 °F	ASTM D 638
	0.300 J/cm @Temperature 23.0 °C	0.562 ft-lb/in @Temperature 73.4 °F	ASTM D 256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	67.0 °C	153 °F	120°C/hr; ASTM D 648
Vicat Softening Point	85.0 °C @Load 5.00 kg	185 °F @Load 11.0 lb	50°C/hr; ASTM D 1525
Flammability, UL94	HB	HB	

Thermal Properties	@Thickness 1.60 mm Metric	@Thickness 0.0630 in English	Comments
	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China