

Cossa Polimeri ESTASTIR HG 0808 Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Molded, Unreinforced

Material Notes:

High gloss polystyrene High impact resistance, good physical and mechanical characteristics, good processability Information provided by Cossa Polimeri S.r.l.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTASTIR-HG-0808-Polystyrene.php

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in ³	ASTM D 792
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ASTM D 955
Melt Flow	6.0 g/10 min @Load 5.00 kg, Temperature 200 °C	6.0 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	25.0 MPa	3630 psi	ASTM D 638
Tensile Strength, Yield	29.0 MPa	4210 psi	ASTM D 638
Elongation at Break	40 %	40 %	ASTM D 638
Flexural Modulus	2.00 GPa	290 ksi	ASTM D 790
Izod Impact, Notched	0.500 J/cm @Temperature 0.000 °C	0.937 ft-lb/in @Temperature 32.0 °F	ASTM D 638
	0.700 J/cm @Temperature 23.0 °C	1.31 ft-lb/in @Temperature 73.4 °F	ASTM D 256

Thermal Properties	Metric	English	Comments
Vicat Softening Point	88.0 °C @Load 5.00 kg	190 °F @Load 11.0 lb	50°C/hr; ASTM D 1525
	96.0 °C @Load 0.999 kg	205 °F @Load 2.20 lb	50°C/hr; ASTM D 1525
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
	HB	HB	

Thermal Properties	@Thickness 3.20 mm Metric	@Thickness 0.126 in English	Comments
--------------------	------------------------------	--------------------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China