

Cotronics Duralco™ 126 450°F (230°C) Silver Filled Epoxy

Category : Polymer , Thermoset , Epoxy

Material Notes:

Two component, silver-filled epoxy for hi-power applications. Cures with mild heat.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cotronics-Duralco-126-450F-230C-Silver-Filled-Epoxy.php

Physical Properties	Metric	English	Comments
Viscosity	15000 cP	15000 cP	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	7.20 W/m-K	50.0 BTU-in/hr-ft ² -°F	
Maximum Service Temperature, Air	232 °C	450 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	0.0020 ohm-cm	0.0020 ohm-cm	

Processing Properties	Metric	English	Comments
Cure Time	10.0 min	0.167 hour	
	@Temperature 162 °C	@Temperature 324 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China