

Cotronics Resbond™ 954 High Temperature Ceramic Adhesive, Stainless Steel Composition

Category : Ceramic

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cotronics-Resbond-954-High-Temperature-Ceramic-Adhesive-Stainless-Steel-Composition.php

Mechanical Properties	Metric	English	Comments
Flexural Strength	17.2 MPa	2500 psi	
Compressive Strength	31.0 MPa	4500 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	18.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	10.0 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Thermal Conductivity	1.44 W/m-K	10.0 BTU-in/hr-ft ² -°F	
Maximum Service Temperature, Air	1090 °C	2000 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China