

Covestro Apec® 1745 Polycarbonate

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Molded

Material Notes:

Easy to demold suitable for superheated steam sterilization up to 143 °C as well as for pharmaceutical applications according to United States Pharmacopeia (USP) XXII Class VI softening temperature (VST/B 120)=170 °C Preprocessing Max. Water content

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Apec-1745-Polycarbonate.php

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in ³	ISO 1183
	0.995 g/cc @Temperature 330 °C	0.0359 lb/in ³ @Temperature 626 °F	Melt
Water Absorption	0.30 %	0.30 %	Similar to ISO 62
Moisture Absorption at Equilibrium	0.12 %	0.12 %	Similar to ISO 62
Melt Flow	17 g/10 min	17 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 330 °C	@Load 4.76 lb, Temperature 626 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	70.0 MPa	10200 psi	ISO 527-1/-2
Elongation at Break	>= 50 %	>= 50 %	Nominal; ISO 527-1/-2
Elongation at Yield	6.4 %	6.4 %	ISO 527-1/-2
Tensile Modulus	2.40 GPa	348 ksi	ISO 527-1/-2
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	ISO 179/1eU
Impact	5500	5500	Puncture - maximum force (N); ISO 6603-2
	6400 @Temperature -30.0 °C	6400 @Temperature -22.0 °F	Puncture - maximum force (N); ISO 6603-2
Puncture Energy	60.0 J	44.3 ft-lb	ISO 6603-2
	65.0 J @Temperature -30.0 °C	47.9 ft-lb @Temperature -22.0 °F	ISO 6603-2

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	38.9 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ISO 11359-1/-2
CTE, linear, Transverse to Flow	70.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	38.9 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ISO 11359-1/-2
Specific Heat Capacity	1.70 J/g $\cdot^\circ\text{C}$	0.406 BTU/lb $\cdot^\circ\text{F}$	Melt
Thermal Conductivity	0.169 W/m-K	1.17 BTU-in/hr-ft ² - $^\circ\text{F}$	Melt
Deflection Temperature at 0.46 MPa (66 psi)	160 $^\circ\text{C}$	320 $^\circ\text{F}$	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	146 $^\circ\text{C}$	295 $^\circ\text{F}$	ISO 75-1/-2
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	IEC 60695-11-10
Oxygen Index	25 %	25 %	ISO 4589-1/-2

Optical Properties	Metric	English	Comments
Transmission, Visible	80 %	80 %	transparent; thickness unknown

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00\text{e}+13$ ohm-cm	$\geq 1.00\text{e}+13$ ohm-cm	IEC 60093
Surface Resistance	$\geq 1.00\text{e}+15$ ohm	$\geq 1.00\text{e}+15$ ohm	IEC 60093
Dielectric Constant	3.0 @Frequency 100 Hz	3.0 @Frequency 100 Hz	IEC 60250
	3.0 @Frequency 1.00e+6 Hz	3.0 @Frequency 1.00e+6 Hz	IEC 60250
Dielectric Strength	35.0 kV/mm	889 kV/in	IEC 60243-1
Dissipation Factor	0.00070 @Frequency 100 Hz	0.00070 @Frequency 100 Hz	IEC 60250
	0.0080 @Frequency 1.00e+6 Hz	0.0080 @Frequency 1.00e+6 Hz	IEC 60250
Comparative Tracking Index	275 V	275 V	IEC 60112

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Melt Temperature Processing Properties	320 - 340 °C Metric	608 - 644 °F English	Comments
	330 °C	626 °F	Injection Molding; ISO 294
Mold Temperature	100 °C	212 °F	Injection Molding; ISO 10724
	110 - 130 °C	230 - 266 °F	
Ejection Temperature	150 °C	302 °F	
Injection Velocity	200 mm/sec	7.87 in/sec	ISO 294

Descriptive Properties	Value	Comments
Availability	Europe	
	Near East/Africa	
	North America	
	South and Central America	
Eff. thermal diffusivity (m ² /s)	1E-07	
Feature	Release agent	
Form	Pellets	
Process	Film Extrusion	
	Injection Molding	
	Profile Extrusion	
	Sheet Extrusion	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China