

Covestro Apec® DP 1-9349/5 Polycarbonate (discontinued **)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Molded

Material Notes:

Key Features:Release agentUnfilledSuitable processing methods:Injection moldingThermoformingInformation provided by Bayer Polymers.As of 1 September 2015, Bayer MaterialScience was separated from Bayer AG and has officially adopted its new name – Covestro. This product was discontinued prior to the separation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Apec-DP-1-93495-Polycarbonate-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.995 g/cc	0.0359 lb/in ³	Melt
	1.17 g/cc	0.0423 lb/in ³	
Water Absorption	0.40 %	0.40 %	
Moisture Absorption at Equilibrium	0.20 %	0.20 %	23°C/50% R.H.
Melt Flow	30 g/10 min	30 g/10 min	
	@Load 2.16 kg, Temperature 330 °C	@Load 4.76 lb, Temperature 626 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	65.0 MPa	9430 psi	
Elongation at Break	>= 50 %	>= 50 %	Nominal
Elongation at Yield	7.0 %	7.0 %	
Tensile Modulus	2.30 GPa	334 ksi	
Charpy Impact Unnotched	NB	NB	
	NB	NB	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.900 J/cm ²	4.28 ft-lb/in ²	
	0.900 J/cm ²	4.28 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C	38.9 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	

Thermal Properties	Metric $m/m-^{\circ}C$	English $in/in-^{\circ}F$	Comments
CTE, linear, transverse to Flow	@Temperature 20.0 °C	@Temperature 68.0 °F	
Specific Heat Capacity	1.70 J/g-°C	0.406 BTU/lb-°F	Melt
Thermal Conductivity	0.169 W/m-K	1.17 BTU-in/hr-ft ² -°F	Melt
Deflection Temperature at 0.46 MPa (66 psi)	160 °C	320 °F	
Deflection Temperature at 1.8 MPa (264 psi)	148 °C	298 °F	
Vicat Softening Point	168 °C	334 °F	50°C/h 50N
Flammability, UL94	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	HB	HB	
	@Thickness 3.00 mm	@Thickness 0.118 in	
Oxygen Index	24 %	24 %	

Optical Properties	Metric	English	Comments
Transmission, Visible	80 %	80 %	Manufacturer states transparent but does not quantify

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00e+13$ ohm-cm	$\geq 1.00e+13$ ohm-cm	
Surface Resistance	$\geq 1.00e+15$ ohm	$\geq 1.00e+15$ ohm	
Dielectric Constant	3.0	3.0	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	35.0 kV/mm	889 kV/in	
	0.0020	0.0020	
Dissipation Factor	@Frequency 100 Hz	@Frequency 100 Hz	
	0.0080	0.0080	
Comparative Tracking Index	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	600 V	600 V	

Processing Properties	Metric	English	Comments
Melt Temperature	330 °C	626 °F	Injection Molding
Mold Temperature	100 °C	212 °F	Injection Molding
Ejection Temperature	150 °C	302 °F	
Injection Velocity	200 mm/sec	7.87 in/sec	

Descriptive Properties	Value	Comments
Effective thermal diffusivity	0.1E-6 m ² /s	Melt

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China