

## Covestro Apec® DP 1-9379/7 Polycarbonate (discontinued \*\*)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Molded

### Material Notes:

Key Features:Release agentUnfilledU.V. stabilized or stable to weatherSuitable processing methods:Injection

moldingThermoformingInformation provided by Bayer Polymers.As of 1 September 2015, Bayer MaterialScience was separated from Bayer AG and has officially adopted its new name – Covestro. This product was discontinued prior to the separation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Covestro-Apec-DP-1-93797-Polycarbonate-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Covestro-Apec-DP-1-93797-Polycarbonate-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in <sup>3</sup>	
Water Absorption	0.40 %	0.40 %	
Moisture Absorption at Equilibrium	0.20 %	0.20 %	23°C/50% R.H.
Melt Flow	7.5 g/10 min @Load 2.16 kg, Temperature 330 °C	7.5 g/10 min @Load 4.76 lb, Temperature 626 °F	cm <sup>3</sup> /10 min.

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	65.0 MPa	9430 psi	
Elongation at Break	50 %	50 %	Nominal
Elongation at Yield	7.0 %	7.0 %	
Tensile Modulus	2.30 GPa	334 ksi	
Charpy Impact Unnotched	NB	NB	
	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	
Charpy Impact, Notched	0.600 J/cm <sup>2</sup>	2.86 ft-lb/in <sup>2</sup>	
	0.600 J/cm <sup>2</sup> @Temperature -30.0 °C	2.86 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C	38.9 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
	70.0 µm/m-°C	38.9 µin/in-°F	

CTE, linear, Transverse to Flow Thermal Properties	Metric @ Temperature 20.0 °C	English @ Temperature 68.0 °F	Comments
Deflection Temperature at 0.46 MPa (66 psi)	191 °C	376 °F	
Deflection Temperature at 1.8 MPa (264 psi)	172 °C	342 °F	
Vicat Softening Point	202 °C	396 °F	50°C/h 50N
Flammability, UL94	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	HB	HB	
	@Thickness 3.00 mm	@Thickness 0.118 in	
Oxygen Index	24 %	24 %	

Optical Properties	Metric	English	Comments
Transmission, Visible	80 %	80 %	Manufacturer states transparent but does not quantify

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+13 ohm-cm	>= 1.00e+13 ohm-cm	
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	
Dielectric Constant	2.9	2.9	
	@Frequency 100 Hz	@Frequency 100 Hz	
	2.9	2.9	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	35.0 kV/mm	889 kV/in	
Dissipation Factor	0.0020	0.0020	
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.0070	0.0070	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	600 V	600 V	

Processing Properties	Metric	English	Comments
Melt Temperature	330 °C	626 °F	Injection Molding
Mold Temperature	100 °C	212 °F	Injection Molding

Processing Properties

Metric **n/sec**

English **sec**

Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China