

Covestro Bayblend® FR3000 BBS081 PC/ABS Blend

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Main characteristics:• High toughness even at low temperatures• High dimensional accuracy and stability• Good paintability• Good flowability
Grade characteristics:• Flame-retardant• Improved chemical resistance• Injection molding
As of 1 September 2015, Bayer MaterialScience was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Bayblend-FR3000-BBS081-PCABS-Blend.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	ISO 1183-1
Moisture Absorption at Equilibrium	0.20 %	0.20 %	ISO 62, 50% RH
Water Absorption at Saturation	0.50 %	0.50 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.00 mm	0.0050 - 0.0070 in/in @Thickness 0.118 in	150x105x3mm; b.o. ISO 2577
Linear Mold Shrinkage, Transverse	0.0050 - 0.0070 cm/cm @Thickness 3.00 mm	0.0050 - 0.0070 in/in @Thickness 0.118 in	150x105x3mm; b.o. ISO 2577

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	45.0 MPa	6530 psi	50 mm/min; ISO 527-1,-2
Tensile Strength, Yield	60.0 MPa	8700 psi	50 mm/min; ISO 527-1,-2
Elongation at Break	>= 40 %	>= 40 %	50 mm/min; b.o. ISO 527-1,-2
Elongation at Yield	3.5 %	3.5 %	50 mm/min; ISO 527-1,-2
Tensile Modulus	2.70 GPa	392 ksi	1 mm/min; ISO 527-1,-2
Izod Impact, Notched (ISO)	10.0 kJ/m ² @Temperature -30.0 °C	4.76 ft-lb/in ² @Temperature -22.0 °F	ISO 180-A
	40.0 kJ/m ² @Temperature 23.0 °C	19.0 ft-lb/in ² @Temperature 73.4 °F	ISO 180-A
Izod Impact, Unnotched (ISO)	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 180-U

Thermal Properties	Metric	English	Comments
	76.0 µm/m-°C	42.2 µin/in-°F	

Thermal Properties	Metric	English	Comments
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	
CTE, linear, Transverse to Flow	80.0 µm/m-°C @Temperature 23.0 - 55.0 °C	44.4 µin/in-°F @Temperature 73.4 - 131 °F	ISO 11359-1,-2
Deflection Temperature at 0.46 MPa (66 psi)	92.0 °C	198 °F	ISO 75-1,-2
Deflection Temperature at 1.8 MPa (264 psi)	82.0 °C	180 °F	ISO 75-1,-2
Vicat Softening Point	95.0 °C @Load 5.10 kg	203 °F @Load 11.2 lb	50°C/h; ISO 306
	97.0 °C @Load 5.10 kg	207 °F @Load 11.2 lb	120°C/h; ISO 306
Flammability, UL94	V-0 @Thickness 1.50 mm	V-0 @Thickness 0.0591 in	
	5VB @Thickness 2.00 mm	5VB @Thickness 0.0787 in	
	5VA @Thickness 3.00 mm	5VA @Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	IEC 60093
Dielectric Constant	3.1 @Frequency 1.00e+6 Hz	3.1 @Frequency 1.00e+6 Hz	IEC 60250
	3.2 @Frequency 100 Hz	3.2 @Frequency 100 Hz	IEC 60250
Dielectric Strength	35.0 kV/mm @Thickness 1.00 mm	889 kV/in @Thickness 0.0394 in	IEC 60243-1
Dissipation Factor	0.0050 @Frequency 100 Hz	0.0050 @Frequency 100 Hz	IEC 60250
	0.0060 @Frequency 1.00e+6	0.0060 @Frequency 1.00e+6	IEC 60250

Electrical Properties	Hz Metric	Hz English	Comments
Comparative Tracking Index	350 V	350 V	Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	240 °C	464 °F	Injection molding; ISO 294
Mold Temperature	80.0 °C	176 °F	Injection molding; ISO 294
Injection Velocity	240 mm/sec	9.45 in/sec	ISO 294

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China