

Covestro Bayblend® KU 2-1480 Polycarbonate/ABS Blend

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Increased thermal stability during processing, slightly higher modulus of elasticity and slightly decreased low-temperature toughness compared to BAYBLEND T 65 MN. Information provided by Bayer. As of 1 September 2015, Bayer MaterialScience was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Bayblend-KU-2-1480-PolycarbonateABS-Blend.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	
Water Absorption	0.70 %	0.70 %	Saturation in water
Moisture Absorption at Equilibrium	0.20 %	0.20 %	Equilibrium at 50% RH
Water Absorption at Saturation	0.70 %	0.70 %	
Melt Flow	11 g/10 min @Load 5.00 kg, Temperature 260 °C	11 g/10 min @Load 11.0 lb, Temperature 500 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	55.0 MPa	7980 psi	
Elongation at Break	>= 50 %	>= 50 %	Nominal
Elongation at Yield	4.0 %	4.0 %	
Tensile Modulus	2.30 GPa	334 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C @Temperature 20.0 °C	38.9 µin/in-°F @Temperature 68.0 °F	
CTE, linear, Transverse to Flow	74.0 µm/m-°C @Temperature 20.0 °C	41.1 µin/in-°F @Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	120 °C	248 °F	
Deflection Temperature at 1.8 MPa (264 psi)	104 °C	219 °F	
Vicat Softening Point	116 °C	241 °F	

Thermal Properties	Metric	English	Comments
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Oxygen Index	23 %	23 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	$\geq 1.00 \times 10^{15}$ ohm-cm	$\geq 1.00 \times 10^{15}$ ohm-cm	
Surface Resistance	1.00×10^{14} ohm	1.00×10^{14} ohm	
Dielectric Constant	2.0	2.0	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	2.9	2.9	
	@Frequency 1×10^6 Hz	@Frequency 1×10^6 Hz	
Comparative Tracking Index	300 V	300 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China