

Covestro Bayblend® T85 SG PC/ABS Blend

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Main characteristics:• High toughness even at low temperatures• High dimensional accuracy and stability• Good paintability• Good flowability
Grade characteristics:• Injection molding• High melt flow
As of 1 September 2015, Bayer Material Science was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Bayblend-T85-SG-PCABS-Blend.php

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in ³	ISO 1183-1
Moisture Absorption at Equilibrium	0.20 %	0.20 %	ISO 62, 50% RH
Water Absorption at Saturation	0.60 %	0.60 %	ISO 62
Viscosity	255000 cP @Shear Rate 1000 1/s, Temperature 260 °C	255000 cP @Shear Rate 1000 1/s, Temperature 500 °F	melt viscosity; b.o. ISO 11443-A
Linear Mold Shrinkage, Flow	0.0055 - 0.0075 cm/cm @Thickness 3.00 mm	0.0055 - 0.0075 in/in @Thickness 0.118 in	150x105x3mm; b.o. ISO 2577
Linear Mold Shrinkage, Transverse	0.0055 - 0.0075 cm/cm @Thickness 3.00 mm	0.0055 - 0.0075 in/in @Thickness 0.118 in	150x105x3mm; b.o. ISO 2577

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	54.0 MPa	7830 psi	50 mm/min; ISO 527-1,-2
Tensile Strength, Yield	55.0 MPa	7980 psi	50 mm/min; ISO 527-1,-2
Elongation at Break	>= 50 %	>= 50 %	50 mm/min; b.o. ISO 527-1,-2
Elongation at Yield	4.9 %	4.9 %	50 mm/min; ISO 527-1,-2
Tensile Modulus	2.30 GPa	334 ksi	1 mm/min; ISO 527-1,-2
Izod Impact, Notched (ISO)	40.0 kJ/m ² @Temperature -30.0 °C	19.0 ft-lb/in ² @Temperature -22.0 °F	ISO 180-A
	50.0 kJ/m ² @Temperature 23.0 °C	23.8 ft-lb/in ² @Temperature 73.4 °F	ISO 180-A
Izod Impact, Unnotched (ISO)	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 180-U

Mechanical Properties	Metric	English	Comments
	@Temperature -30.0 °C	@Temperature -22.0 °F	ISO 180-U
Puncture Energy	46.0 J	33.9 ft-lb	ISO 6603-2
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	52.0 J	38.4 ft-lb	ISO 6603-2
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	75.0 µm/m-°C	41.7 µin/in-°F	ISO 11359-1,-2
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	
CTE, linear, Transverse to Flow	70.0 µm/m-°C	38.9 µin/in-°F	ISO 11359-1,-2
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	
Deflection Temperature at 0.46 MPa (66 psi)	128 °C	262 °F	ISO 75-1,-2
Deflection Temperature at 1.8 MPa (264 psi)	108 °C	226 °F	ISO 75-1,-2
Vicat Softening Point	129 °C	264 °F	50°C/h; ISO 306
	@Load 5.10 kg	@Load 11.2 lb	
	130 °C	266 °F	120°C/h; ISO 306
	@Load 5.10 kg	@Load 11.2 lb	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+17 ohm-cm	1.00e+17 ohm-cm	IEC 60093
Surface Resistance	1.00e+17 ohm	1.00e+17 ohm	IEC 60093
Dielectric Constant	2.9	2.9	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.0	3.0	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	35.0 kV/mm	889 kV/in	IEC 60243-1
	@Thickness 1.00 mm	@Thickness 0.0394 in	
	0.0025	0.0025	

Dielectric Factor Electrical Properties	Metric @Frequency 100 Hz	English @Frequency 100 Hz	IEC 60250 Comments
	0.0090	0.0090	
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	IEC 60250
Comparative Tracking Index	200 V	200 V	Solution A; IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China