

Covestro Bayblend® T85 XF Polycarbonate + ABS

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

General purpose injection molding grade Vicat/B 120 temperature = 130°C better flow than T85 Preprocessing Max. Water content

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Bayblend-T85-XF-Polycarbonate-ABS.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ISO 1183
	0.980 g/cc	0.0354 lb/in ³	Melt
	@Temperature 260 °C	@Temperature 500 °F	
Water Absorption	0.70 %	0.70 %	Similar to ISO 62
Moisture Absorption at Equilibrium	0.20 %	0.20 %	Similar to ISO 62
Melt Flow	19 g/10 min	19 g/10 min	ISO 1133
	@Load 5.00 kg, Temperature 260 °C	@Load 11.0 lb, Temperature 500 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	54.0 MPa	7830 psi	ISO 527-1/-2
Elongation at Yield	4.7 %	4.7 %	ISO 527-1/-2
Tensile Modulus	2.30 GPa	334 ksi	ISO 527-1/-2

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	75.0 µm/m-°C	41.7 µin/in-°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	80.0 µm/m-°C	44.4 µin/in-°F	ISO 11359-1/-2
Specific Heat Capacity	1.73 J/g-°C	0.413 BTU/lb-°F	Melt
Thermal Conductivity	0.154 W/m-K	1.07 BTU-in/hr-ft ² -°F	Melt
Deflection Temperature at 0.46 MPa (66 psi)	127 °C	261 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	109 °C	228 °F	ISO 75-1/-2
Vicat Softening Point	128 °C	262 °F	50°C/h 50N; ISO 306
Flammability, UL94	HB	HB	IEC 60695-11-10

Thermal Properties	@Thickness 0.900 mm Metric	@Thickness 0.0354 in English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+13 ohm-cm	>= 1.00e+13 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	IEC 60093
Dielectric Constant	3.0	3.0	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	3.1	3.1	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	35.0 kV/mm	889 kV/in	IEC 60243-1
Dissipation Factor	0.0020	0.0020	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Comparative Tracking Index	0.0085	0.0085	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	225 V	225 V	IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	240 - 280 °C	464 - 536 °F	
	260 °C	500 °F	
Mold Temperature	60.0 - 80.0 °C	140 - 176 °F	Injection Molding; ISO 294
	80.0 °C	176 °F	
Ejection Temperature	130 °C	266 °F	
Injection Velocity	240 mm/sec	9.45 in/sec	ISO 294

Descriptive Properties	Value	Comments
Availability	Asia Pacific	
	Europe	
	Near East/Africa	
	North America	
	South and Central America	

Descriptive Properties (m ² /s)	Value -08	Comments
Feature	Release agent	
Form	Pellets	
Process	Injection Molding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China