

Covestro Bayflex® 190 Polyurethane Elastomeric RIM, 20% Mica Filled, MDI-based 2-Component Liquid System

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Glass Filled , Rubber or Thermoset Elastomer (TSE)

Material Notes:

0.150 in. thickness. RIM = Reaction Injection Molding Information provided by Bayer Corporation, Polyurethanes Division As of 1 September 2015, Bayer Material Science was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Bayflex-190-Polyurethane-Elastomeric-RIM-20-Mica-Filled-MDI-based-2-Component-Liquid-System.php

Physical Properties	Metric	English	Comments
Density	1.25 g/cc	0.0452 lb/in ³	ASTM D792
Water Absorption at Saturation	0.10 %	0.10 %	240 hours; Bayer Test
Linear Mold Shrinkage	0.0075 cm/cm	0.0075 in/in	Bayer Test

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	38.0 MPa	5510 psi	ASTM D638/D412
Elongation at Break	15 %	15 %	ASTM D638/D412
Flexural Modulus	1.72 GPa	249 ksi	ASTM D790
Izod Impact, Notched	0.500 J/cm	0.937 ft-lb/in	ASTM D256
Tear Strength	122 kN/m	696 pli	Die C; ASTM D624

Thermal Properties	Metric	English	Comments
CTE, linear	137 µm/m-°C	76.1 µin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Flammability, UL94	HB	HB	
	@Thickness 3.18 mm	@Thickness 0.125 in	
	HB	HB	
	@Thickness 3.18 mm	@Thickness 0.125 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China