

Covestro Desmopan® 795 U Polyurethane

Category : Polymer , Thermoplastic , Polyurethane, TP

Material Notes:

injection molding gradewith special UV stabilizersgood hydrolysis and microbial resistanceshort cycle timesApplicationEar-
tagsPreprocessingMax. Water content

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Desmopan-795-U-Polyurethane.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	94	94	3s; ISO 868
Hardness, Shore D	43	43	15s; ISO 868
Abrasion	25	25	mm ³ ; ISO 4649
Compression Set	22 %	22 %	ISO 815
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	42 %	42 %	ISO 815
	@Temperature 70.0 °C	@Temperature 158 °F	

Descriptive Properties	Value	Comments
Availability	Asia Pacific	
	Europe	
	India	
	Near East/Africa	
	South and Central America	
Feature	Release agent	
Form	Pellets	
Process	Injection Molding	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China