

Covestro Desmopan® DP 8798A S043 Polyurethane

Category : Polymer , Thermoplastic , Polyurethane, TP

Material Notes:

PreprocessingMax. Water content

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Desmopan-DP-8798A-S043-Polyurethane.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	96	96	3s; ISO 868
Hardness, Shore D	53	53	15s; ISO 868
Tensile Strength at Break	65.0 MPa	9430 psi	ISO 527-1/-2
Tensile Strength, Yield	65.0 MPa	9430 psi	parallel; ISO 527-3
	17.0 MPa @Strain 100 %	2470 psi @Strain 100 %	ISO 527-1/-2
	39.0 MPa @Strain 300 %	5660 psi @Strain 300 %	ISO 527-1/-2
Elongation at Break	>= 300 %	>= 300 %	ISO 527-1/-2
Abrasion	15	15	mm ³ ; ISO 4649
Compression Set	25 % @Temperature 23.0 °C	25 % @Temperature 73.4 °F	ISO 815
	45 % @Temperature 70.0 °C	45 % @Temperature 158 °F	ISO 815

Descriptive Properties	Value	Comments
Availability	Asia Pacific	
	India	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China