

## Covestro Desmopan® DP 9386A Polyurethane

Category : Polymer , Thermoplastic , Polyurethane, TP

**Material Notes:**

Extrusion- and injection molding gradevery good hydrolysis and microbial resistancegood low-temperature flexibilitycomplies with VDE 0282-10very large processing windowApplicationCable sheathingsHosesnon-reinforcedProfilesAs of 1 September 2015, Bayer MaterialScience was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Covestro-Desmopan-DP-9386A-Polyurethane.php](http://www.lookpolymers.com/polymer_Covestro-Desmopan-DP-9386A-Polyurethane.php)

Physical Properties	Metric	English	Comments
Density	1.11 g/cc	0.0401 lb/in <sup>3</sup>	ISO 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85	85	3s; ISO 868
Hardness, Shore D	34	34	15s; ISO 868
Abrasion	84	84	mm <sup>3</sup> ; ISO 4649
Compression Set	28 %	28 %	ISO 815
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	36 %	36 %	ISO 815
	@Temperature 70.0 °C	@Temperature 158 °F	

Descriptive Properties	Value	Comments
Availability	Europe	
	Near East/Africa	
	South and Central America	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China