

Covestro Makroblend® UT5205 PC/PBT Blend

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Unreinforced , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Main characteristics:• High toughness even at low temperatures• Good chemical resistance• Good paintability• Good flowability• Low moisture intake
Grade characteristics:• Impact modified• Suitable for metal insert molding
As of 1 September 2015, Bayer Material Science was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Makroblend-UT5205-PCPBT-Blend.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	ISO 1183-1
Linear Mold Shrinkage, Flow	0.0070 - 0.0090 cm/cm	0.0070 - 0.0090 in/in	b.o. ISO 2577
Linear Mold Shrinkage, Transverse	0.0070 - 0.0090 cm/cm	0.0070 - 0.0090 in/in	b.o. ISO 2577

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	45.0 MPa	6530 psi	50 mm/min; ISO 527-1,-2
Tensile Strength, Yield	55.0 MPa	7980 psi	50 mm/min; ISO 527-1,-2
Elongation at Break	>= 50 %	>= 50 %	Nominal, 50 mm/min; ISO 527-1,-2
Elongation at Yield	4.5 %	4.5 %	50 mm/min; ISO 527-1,-2
Tensile Modulus	2.00 GPa	290 ksi	1 mm/min; ISO 527-1,-2
Flexural Modulus	2.00 GPa	290 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	45.0 kJ/m ² @Temperature -20.0 °C	21.4 ft-lb/in ² @Temperature -4.00 °F	ISO 180-A
	60.0 kJ/m ² @Temperature 23.0 °C	28.6 ft-lb/in ² @Temperature 73.4 °F	ISO 180-A

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	90.0 µm/m-°C	50.0 µin/in-°F	ISO 11359-1,-2
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	
CTE, linear, Transverse to Flow	90.0 µm/m-°C	50.0 µin/in-°F	ISO 11359-1,-2
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	75.0 °C	167 °F	ISO 75-1,-2
Vicat Softening Point	122 °C @Load 5.10 kg	252 °F @Load 11.2 lb	120°C/h; ISO 306
Shrinkage	0.10 - 0.20 %	0.10 - 0.20 %	post-shrinkage; b.o. ISO 2577

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	IEC 60093
Dielectric Constant	3.1 @Frequency 1.00e+6 Hz	3.1 @Frequency 1.00e+6 Hz	IEC 60250
	3.2 @Frequency 100 Hz	3.2 @Frequency 100 Hz	IEC 60250
Dissipation Factor	0.0030 @Frequency 100 Hz	0.0030 @Frequency 100 Hz	IEC 60250
	0.015 @Frequency 1.00e+6 Hz	0.015 @Frequency 1.00e+6 Hz	IEC 60250
Comparative Tracking Index	100 V	100 V	CTI M; Solution B; IEC 60112
	225 V	225 V	Solution A; IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China