

Covestro Makrolon® 2407 Polycarbonate, Injection Grade

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Unreinforced, Flame Retardant

Material Notes:

Very easy flowing injection molding grade with easy mold release and UV stabilizer. Information provided by Bayer. As of 1 September 2015, Bayer MaterialScience was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Makrolon-2407-Polycarbonate-Injection-Grade.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	
Water Absorption	0.35 %	0.35 %	Saturation in water
Moisture Absorption at Equilibrium	0.15 %	0.15 %	Equilibrium at 50% RH
Water Absorption at Saturation	0.35 %	0.35 %	
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	19 g/10 min @Load 1.20 kg, Temperature 300 °C	19 g/10 min @Load 2.65 lb, Temperature 572 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	75	75	ASTM D785
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Ultimate	69.0 MPa	10000 psi	ASTM D638
Tensile Strength, Yield	63.0 MPa	9140 psi	
Elongation at Break	120 %	120 %	ASTM D638
Elongation at Yield	6.0 %	6.0 %	
Tensile Modulus	2.30 GPa	334 ksi	
Flexural Yield Strength	83.0 MPa	12000 psi	at 5% strain; ASTM D790
Flexural Modulus	2.30 GPa	334 ksi	ASTM D790
Izod Impact, Notched	7.50 J/cm @Thickness 3.20 mm	14.1 ft-lb/in @Thickness 0.126 in	ASTM D256
Charpy Impact Unnotched	NB	NB	
Tensile Creep Modulus, 1 hour			

Mechanical Properties	2200 MPa Metric	319000 psi English	Comments
Tensile Creep Modulus, 1000 hours	1900 MPa	276000 psi	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	38.9 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	70.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	38.9 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Specific Heat Capacity	1.17 $\text{J}/\text{g}\cdot\text{°C}$	0.280 $\text{BTU}/\text{lb}\cdot\text{°F}$	ASTM D2766
Thermal Conductivity	0.200 $\text{W}/\text{m}\cdot\text{K}$	1.39 $\text{BTU}\cdot\text{in}/\text{hr}\cdot\text{ft}^2\cdot\text{°F}$	ASTM C177
Deflection Temperature at 0.46 MPa (66 psi)	137 °C	279 °F	
Deflection Temperature at 1.8 MPa (264 psi)	124 °C	255 °F	
Vicat Softening Point	144 °C	291 °F	
Glass Transition Temp, Tg	148 °C	298 °F	
UL RTI, Electrical	125 °C	257 °F	
UL RTI, Mechanical with Impact	115 °C	239 °F	
UL RTI, Mechanical without Impact	125 °C	257 °F	
Flammability, UL94	V-2	V-2	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-2	V-2	
	@Thickness 2.60 mm	@Thickness 0.102 in	
Oxygen Index	26 %	26 %	

Optical Properties	Metric	English	Comments
Refractive Index	1.584	1.584	
Haze	1.0 %	1.0 %	ASTM D1003
	@Thickness 3.20 mm	@Thickness 0.126 in	
Transmission, Visible	88 %	88 %	ASTM D1003
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	$\geq 1.00 \times 10^{15}$ ohm-cm	$\geq 1.00 \times 10^{15}$ ohm-cm	
Surface Resistance	1.00×10^{15} ohm	1.00×10^{15} ohm	
Dielectric Constant	2.9	2.9	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	3.0	3.0	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	30.0 kV/mm	762 kV/in	
Dissipation Factor	0.0010	0.0010	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dissipation Factor	0.010	0.010	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Arc Resistance	120 sec	120 sec	Tungsten Electrodes; ASTM D495
Comparative Tracking Index	275 V	275 V	
Hot Wire Ignition, HWI	15 - 30 sec	15 - 30 sec	UL Rating PLC 3 (15-30 sec)
	@Thickness 3.00 mm	@Thickness 0.118 in	
High Amp Arc Ignition, HAI	15 - 30 arcs	15 - 30 arcs	UL Rating PLC 3 (15-30 arcs)
	@Thickness 3.00 mm	@Thickness 0.118 in	
High Voltage Arc-Tracking Rate, HVTR	≤ 10.0 mm/min	≤ 0.394 in/min	UL Rating PLC 0 (<10 mm/min.)
	@Thickness 3.00 mm	@Thickness 0.118 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China