

Covestro Makrolon® DP 1-1413 Polycarbonate, Gamma Radiation Stabilized

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Gamma Radiation Resistant

Material Notes:

Medium viscosity grade suitable for sterilization with hot-air and gamma radiation, specially suitable for medical equipment (dialyser housings). Information provided by Bayer. As of 1 September 2015, Bayer Material Science was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Makrolon-DP-1-1413-Polycarbonate-Gamma-Radiation-Stabilized.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	
Water Absorption	0.35 %	0.35 %	Saturation in water
Moisture Absorption at Equilibrium	0.15 %	0.15 %	Equilibrium at 50% RH
Water Absorption at Saturation	0.35 %	0.35 %	
Melt Flow	10 g/10 min @Load 1.20 kg, Temperature 300 °C	10 g/10 min @Load 2.65 lb, Temperature 572 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	65.0 MPa	9430 psi	
Elongation at Break	>= 50 %	>= 50 %	Nominal
Elongation at Yield	6.0 %	6.0 %	
Tensile Modulus	2.40 GPa	348 ksi	
Charpy Impact Unnotched	NB	NB	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C	38.9 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	70.0 µm/m-°C	38.9 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Vicat Softening Point	145 °C	293 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China