

Covestro Makrolon® ET UV120 Polycarbonate

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Extruded

Material Notes:

Main characteristics:• High toughness• Good heat resistance• Glass-like transparency, optical quality• High dimensional accuracy and stability
Grade characteristics:• PC/UV absorber concentrate• High viscosity; easy release• Special grade for the coextrusion of Makrolon ET base resins
As of 1 September 2015, Bayer Material Science was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Makrolon-ET-UV120-Polycarbonate.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ISO 1183-1
Melt Flow	11 g/10 min @Load 1.20 kg, Temperature 300 °C	11 g/10 min @Load 2.65 lb, Temperature 572 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Charpy Impact Unnotched	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 179-1eU

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	128 °C	262 °F	ISO 75-1,-2
Deflection Temperature at 1.8 MPa (264 psi)	116 °C	241 °F	ISO 75-1,-2
Vicat Softening Point	134 °C @Load 5.10 kg	273 °F @Load 11.2 lb	50°C/h; ISO 306

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	IEC 60093

Processing Properties	Metric	English	Comments
Melt Temperature	300 °C	572 °F	Injection molding; ISO 294
Mold Temperature	80.0 °C	176 °F	Injection molding; ISO 294
Injection Velocity	200 mm/sec	7.87 in/sec	ISO 294

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China