

## Covestro Makrolon® ET UV130 Polycarbonate

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Extruded

### Material Notes:

Main characteristics:• High toughness• Good heat resistance• Glass-like transparency, optical quality• High dimensional accuracy and stability  
Grade characteristics:• PC/UV absorber concentrate• High viscosity; easy release• Special grade for the coextrusion of Makrolon ET base resins  
As of 1 September 2015, Bayer Material Science was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Covestro-Makrolon-ET-UV130-Polycarbonate.php](http://www.lookpolymers.com/polymer_Covestro-Makrolon-ET-UV130-Polycarbonate.php)

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in <sup>3</sup>	ISO 1183-1
Melt Flow	11 g/10 min @Load 1.20 kg, Temperature 300 °C	11 g/10 min @Load 2.65 lb, Temperature 572 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Charpy Impact Unnotched	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 179-1eU

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	127 °C	261 °F	ISO 75-1,-2
Deflection Temperature at 1.8 MPa (264 psi)	115 °C	239 °F	ISO 75-1,-2
Vicat Softening Point	134 °C @Load 5.10 kg	273 °F @Load 11.2 lb	50°C/h; ISO 306

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	IEC 60093

Processing Properties	Metric	English	Comments
Melt Temperature	290 °C	554 °F	Injection molding; ISO 294
Mold Temperature	80.0 °C	176 °F	Injection molding; ISO 294
Injection Velocity	200 mm/sec	7.87 in/sec	ISO 294

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**