

Cresset Powers Cress-Alon™ A2600 2.6 r.v. Compounding Grade Nylon 6, 50% RH

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Neat resin, for compounding. Information provided by Cresset Powers Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cresset-Powers-Cress-Alon-A2600-26-rv-Compounding-Grade-Nylon-6-50-RH.php

Physical Properties	Metric	English	Comments
Density	1.12 - 1.14 g/cc	0.0405 - 0.0412 lb/in ³	ASTM D792
Apparent Bulk Density	>= 0.659 g/cc	>= 0.0238 lb/in ³	
Viscosity Measurement	2.6	2.6	Relative Viscosity
Melt Flow	14 - 20 g/10 min @Load 2.16 kg, Temperature 230 °C	14 - 20 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Thermal Properties	Metric	English	Comments
Melting Point	220 - 224 °C	428 - 435 °F	ASTM DSC
Deflection Temperature at 1.8 MPa (264 psi)	>= 55.0 °C	>= 131 °F	

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.080 %	<= 0.080 %	

Descriptive Properties	Value	Comments
Extractables, wt%	<0.4	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China